

This page is mainly introduced the SA-276 S42010 chemical information, mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, etc. It also contains the use of SA-276 S42010, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

Data Table for Grades Stainless Steels SA-276 S42010

SA-276 S42010 Standard Number:

| ITEM | Standard Number | Descriptions |
|------|-----------------|---|
| 1 | SA-276 | Specification for Stainless Steel Bars and Shapes |

SA-276 S42010 Chemical composition (mass fraction) (wt.%)

| Chemical | Min.(%) | Max.(%) |
|----------|---------|---------|
| C | 0.15 | 0.30 |
| Mn | | 1.00 |
| Si | | 1.00 |
| P | | 0.04 |
| S | | 0.03 |
| Cr | 13.50 | 15.00 |
| Ni | 0.25 | 1.00 |
| Mo | 0.40 | 1.00 |

SA-276 S42010 Physical Properties

| | | |
|------------------|---------|--------------------------|
| Tensile strength | 115-234 | σ_b /MPa |
| Yield Strength | 23 | $\sigma_{0.2} \geq$ /MPa |
| Elongation | 65 | $\delta_5 \geq$ (%) |
| ψ | - | $\psi \geq$ (%) |
| Akv | - | Akv \geq /J |
| HBS | 123-321 | - |
| HRC | 30 | - |

SA-276 S42010 Mechanical Properties

| | | |
|------------------|---------|-----------------|
| Tensile strength | 231-231 | σ_b /MPa |
| | | |

| | | |
|----------------|---------|----------------------------------|
| Yield Strength | 154 | $\sigma_{0.2} \geq / \text{MPa}$ |
| Elongation | 56 | $\delta_5 \geq (\%)$ |
| ψ | - | $\psi \geq (\%)$ |
| Akv | - | $Akv \geq / \text{J}$ |
| HBS | 235-268 | - |
| HRC | 30 | - |

SA-276 S42010 Heat Treatment Regime

| Annealing | Quenching | Tempering | Normalizing | Q & T |
|-----------|-----------|-----------|-------------|-------|
| √ | √ | √ | √ | √ |

SA-276 S42010 Range of products

| Product type | Products | Dimension | Processes | Deliver Status |
|-----------------|--|----------------------------|---|---|
| Plates / Sheets | Plates / Sheets | 0.08-200mm(T)*W*L | Forging, hot rolling and cold rolling | Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting |
| Steel Bar | Round Bar, Flat Bar, Square Bar | $\Phi 8-1200\text{mm} * L$ | Forging, hot rolling and cold rolling, Cast | Black, Rough Turning, Shot Blasting, |
| Coil / Strip | Steel Coil / Steel Strip | 0.03-16.0x1200mm | Cold-Rolled & Hot-Rolled | Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting |
| Pipes / Tubes | Seamless Pipes/Tubes, Welded Pipes/Tubes | OD:6-219mm x WT:0.5-20.0mm | Hot extrusion, Cold Drawn, Welded | Annealed, Solution and Aging, Q+T, ACID-WASHED |

We can produce Stainless Steels the specifications follows:

Note:

- (1) listed in the table apex diameter (d), to steel thickness (a) multiples said.
- (2) in the ASTM A6 standard specified scope can meet any additional conditions.
- (3) from the standard for 50 mm (2 in).

Mechanical properties

Mechanische Eigenschaften

Caracteristiques mecaniques

ReH Minimum yield strength / Mindestwert der oberen Streckgrenze / Limite d'elasticite minimale

Rm Tensile strength / Zugfestigkeit / Resistance a la traction

A Minimum elongation / Mindestwert der Bruchdehnung / Allongement minimal

J Notch impact test / Kerbschlagbiegeversuch / Essai de flexion par choc

Round bar:

Diameter : 1mm-2000mm

Square bar:

Size: 50mm * 50mm-600mm *600mm

Plate steel/flat bar:

Size: Thickness: 0.1mm-800mm Width: 10mm to 1500mm

Tube/pipe:

Size: OD: 6-219mm WT: 1-35 mm.

Cold-rolled sheet: Thickness: 2-5mm Width:1000mm Length: 2000mm

Hot-rolled sheet: Thickness:6-80mm Width: 210-610mm

Length: We can supply any length based on the customer's requirement.

Forging/hot rolling/ extrusion of steel.

Forging: Shafts with flanks/pipes/tubes/slugs/donuts/cubes/other shapes

Finished goods condition: hot forging/hot rolling + annealing/normalizing + tempering/quenching + tempering/any conditions based on the customer's requirement

Surface conditions: scaled (hot working finish)/ground/rough machining/fine machining/based on the customer's requirement

Furnaces for metallurgical processing: electrode arc + LF/VD/VOD/ESR/Vacuum consumable electrode.

Ultrasonic inspection: 100% ultrasonic inspection for any imperfections or based on the customer's requirement.

UTS according to SEP 1921 C/c,D/d,E/e;A388 or GB/T 6402

Excellent service for all kinds of industries, with advantages of technologies, equipment and price.

We serve you with our honesty, integrity, and professionalism.